

# THE INFLUENCE OF THE MAGNETIC FIELD ON THE STRUCTURE AND PHYSICAL PROPERTIES OF EPOXY COMPOSITE MATERIALS

Yuliia Bardadym<sup>1</sup>, Edward Sporyagin<sup>2</sup>, Oleksandr Naumenko<sup>3</sup>

<sup>1</sup> Institute of Macromolecular Chemistry of NAS of Ukraine

<sup>2</sup> Oles Honchar Dnipro National University

<sup>3</sup> Ukrainian State University of Chemical Technology

[yuliia.bardadym@gmail.com](mailto:yuliia.bardadym@gmail.com)

Polymer modifications are intended to impute different, typically desired properties to the new modified material properties such as enhanced thermal stability, strength, ductility, compatibility or degradability, flexibility, rigidity, melting and glass-transition temperatures etc. Physical modification is a directed change in the physical properties of polymers carried out by the transformation of their supramolecular structure under the influence of physical influences.

Physical modification is a simpler and more economical method of obtaining new materials than the synthesis of new polymers [1]. Physical modification of polymers is divided into chemical, physico-chemical and physical methods. The molecular structure of polymers change in physico-chemical modification. And only when using the physical modification the chemical composition and molecular structure are stable [2, 3]. Physical modification of polymers arises under the influence of various force fields (mechanical, electrical, magnetic, etc.) or as a result of thermal effects. The important role in the influence of magnetic field is the processes of orientation of macromolecules [4, 5].

This work is devoted to the study of the effect of external permanent magnetic field on the structure, thermophysical, dielectric properties of epoxy polymers and their composites containing metal oxides.

Samples of nanocomposites were formed from epoxy resin ED-20 and triethylenetetramine. Stoichiometric ratio was 1 mole of epoxy resin to 0,18 mole triethylenetetramine. Powder CdO, PbO and Cr<sub>2</sub>O<sub>3</sub> were used as fillers. The content of metal oxide was 3 vol. %. Samples of nanocomposites were subjected to curing with different conditions. The influence of constant magnetic field was 2·10<sup>5</sup> A/m. All curing processes were done at 293 – 297 K for 24 hours. Then all polymeric samples were carried out temperature stabilization at 333 ± 2 K for 24 hours.

System studies of structure, thermophysical, thermomechanical and dielectric properties of composites filled with diamagnetic or paramagnetic metal oxides formed under the influence of external constant physical field were carried out for the first time. Patterns of connection between the structure and the physical and mechanical properties of epoxy composites were first established.

The introduction of inorganic filler causes the epoxy polymer to dissolution of the structure and reduces the glass transition temperature of the epoxy composite. The estimation of the influence of constant physical fields on the tangent angle of the dielectric losses of the filled composites shows that the orientation effect of constant physical fields increases the free volume of molecular chains of the chemical network of the epoxy polymer. As a result of the directed action of constant physical fields an orientation effect is observed that causes the structure and compaction of macromolecules and inorganic filler in epoxy composites to be streamlined. Also, the gel fraction of the epoxy polymer and its composites was calculated. The values are constant and range from 99,2 % to 97,98 % while the gel fraction of the polyepoxide matrix is 99,97 % to 99,3 %.

The obtained research results can be used as a scientific basis for finding optimal conditions for the formation of the structure of polymer composites filled with dispersed fillers, which will allow obtaining materials with the necessary pre-determined physical, mechanical, electrophysical and thermophysical properties.

- 
- [1] Yu. Golovin, S. Gribanovsky, D. Golovin, N. Klyachko, Towards nanomedicines of the future: remote magneto-mechanical actuation of nanomedicines by alternating magnetic fields, *Journal of Controlled release*, **219**, 43 – 60 (2015).
- [2] F. Cardone, G. Ferrotti, F. Frigio, Influence of polymer modification on asphalt binder dynamic and steady flow viscosities, *Construction and Building Materials*, **71**, 435 – 443 (2014).
- [3] G. M. Su, E. Lim, A. R. Jacobs, Polymer side chain modification alters separation in ferroelectric-semiconductor polymer blends for organic memory, *ACS Macro Letters*, **3** (12), 1244 – 1248 (2014).
- [4] J. Szajnar, M. Stawarz, T. Wrobel, Influence of electromagnetic field on pure metals and alloys structure, *Journal of Achievements in Materials and Manufacturing Engineering*, **34**, 95 – 102 (2009).
- [5] Yu. Bardadym, E. Sporyagin, The influence of the constant physical fields on structure of polymer composites with cadmium oxide and polyaniline, *7<sup>th</sup> International Conference Nanomaterials: Application and Properties*, ISBN 978-1-5386-2810-2, Ukraine, 03NNSA13-1 – 03NNSA13-4 (2017).